



1724
CW

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re the application of)	Mail Stop: AMENDMENT
)	
DROHMANN et al.)	Confirmation No.: 4300
)	
Serial No.: 10/509,641)	Examiner: POPOVICS
)	
Filing or 371(c) Date: 09/29/2004)	Art Unit: 1724

For: USE OF POLYMERS COMPRISING THERMOPLASTIC POLYMERS AS FILTER AIDS AND/OR STABILIZERS

I hereby certify that this correspondence is being deposited with the United States Postal Service with sufficient postage as first class mail in an envelope addressed to Commissioner for Patents, P.O. Box 1450, Alexandria, Virginia 22313-1450, or being facsimile transmitted to the United States Patent and Trademark Office, Fax No. 571-273-8300, on 3-31-06.

Typed or printed name of person signing this certificate:

Signature:

Michelle Bryant
Michelle Bryant

Honorable Commissioner for Patents
Alexandria, Virginia 22313-1450

CLAIM TO PRIORITY

Applicants request entry and consideration of the following verified translation of the priority document for the above mentioned application to perfect priority.

Please charge any shortage in fees due in connection with the filing of this paper to Deposit Account No. 14.1437. Please credit any excess fees to such account.

Respectfully submitted,
NOYAK DRUCE DeLUCA & QUIGG LLP

Jason D. Voight
Jason D. Voight
Reg. No. 42,205

Customer No. 26474
1300 Eye Street, N.W.
400 East Tower
Washington, D.C. 20005
(202) 659-0100
JDV/TRS



UNITED STATES PATENT AND TRADEMARK OFFICE

I, Susan ANTHONY BA, ACIS,

Director of RWS Group Ltd, of Europa House, Marsham Way, Gerrards Cross, Buckinghamshire, England declare;

1. That I am a citizen of the United Kingdom of Great Britain and Northern Ireland.
2. That the translator responsible for the attached translation is well acquainted with the German and English languages.
3. That the attached is, to the best of RWS Group Ltd knowledge and belief, a true translation into the English language of the accompanying copy of the specification filed with the application for a patent in Germany on 5 April 2002 under the number 102 15 147.4 and the official certificate attached hereto.
4. That I believe that all statements made herein of my own knowledge are true and that all statements made on information and belief are true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the patent application in the United States of America or any patent issuing thereon.

For and on behalf of RWS Group Ltd

The 17th day of March 2006

FEDERAL REPUBLIC OF GERMANY

[Eagle crest]

**Priority Certificate
for the filing of a Patent Application**

File Reference: 102 15 147.4

Filing date: 05 April 2002

Applicant/Proprietor: BASF Aktiengesellschaft, Ludwigshafen/DE

Title: Use of polymers comprising thermoplastic polymers as filter aids
and/or stabilizers

IPC: B 01 D, C 12 H, A 23 L

**The attached documents are a correct and accurate reproduction of the original
submission for this Application.**

Munich, 23 January 2003

German Patent and Trademark Office

The President

[Seal of the German Patent
and Trademark Office]

pp

[signature]

Ebert

We claim:

1. The use of polymers comprising
 - (a) from 20 to 95% by weight of at least one thermoplastic polymer
 - (b) from 80 to 5% by weight of at least one further substance selected from the group consisting of silicates, carbonates, oxides, silica gel, kieselguhr, diatomaceous earth, other polymers or mixtures thereofas filter aids and/or stabilizers for filtering and/or stabilizing an aqueous liquid, with the proviso that the thermoplastic polymer set forth under (a) must not be polystyrene.
2. The use of polymers as claimed in claim 1, wherein, in addition to the filtration, stabilization of the aqueous liquid takes place simultaneously.
3. The use of polymers as claimed in claim 1 or 2, wherein the substance set forth under (b) is selected from the group consisting of alkali metal carbonates or alkaline earth metal carbonates, alkali metal hydrogencarbonates or alkaline earth metal hydrogencarbonates, the oxides or mixed oxides of subgroup 4 or subgroup 3, polyamides, crosslinked polyvinyl lactams, polyvinylamines or mixtures thereof.
4. The use of polymers as claimed in one of claims 1 to 3, wherein the substance set forth under (b) is crosslinked polyvinylpolypyrrolidone (PVPP).
5. The use of polymers as claimed in one of claims 1 to 4, wherein the substance set forth under (b) is selected from the group consisting of crosslinked polyvinylpolypyrrolidone, TiO_2 , NaHCO_3 , KHCO_3 , CaCO_3 , silica gel, kieselguhr, diatomaceous earth, bentonite or mixtures thereof.

2

6. A process for filtering and/or stabilizing an aqueous liquid, which comprises using as filter aid or stabilizer a polymer comprising
- 5 (a) from 20 to 95% by weight of at least one thermoplastic polymer
- (b) 80-5% by weight of at least one further substance selected from the group consisting of silicates, carbonates, oxides, silica gel, kieselguhr, diatomaceous earth, further polymers or mixtures thereof, with the proviso that the thermoplastic polymer set forth under (a) must not be polystyrene.
- 10
- 15 7. A process as claimed in claim 6, wherein, in addition to the filtration, simultaneous stabilization of the medium to be filtered takes place.
8. A process as claimed in either of claims 6 and 7, wherein, during the filtration, the precoat filtration technique is used.
- 20
9. The process as claimed in one of claims 6 to 8, wherein the aqueous liquid is a liquid selected from the group consisting of fruit juice drinks or fermented beverages.
- 25
10. A process as claimed in one of claims 6 to 9, wherein the aqueous liquid is beer.
- 30 11. A process as claimed in one of claims 6 to 10, wherein the polymers used have a mean particle size of from 1 to 1000 μm .
12. A process as claimed in one of claims 6 to 11, wherein the particles of the polymers used are not spheroidal.

35

40

45

Use of polymers comprising thermoplastic polymers as filter aids and/or stabilizers

- 5 The present invention relates to the use of polymers comprising thermoplastic polymers as filter aids and/or stabilizers for the filtration and/or stabilization of aqueous liquids.

Separation of solid-liquid mixtures of substances by filtration
10 is an important process step in many industrial production processes. The term filter aid encompasses a number of products which are used in bulk, pulverulent, granulated or fibrous form as precoat material in filtration.

- 15 Filter aids can be applied, before the start of filtration, as auxiliary filter layer (precoat filter) to the filter aid, to achieve a looser cake structure, or can be added continuously to the slurry to be filtered.
- 20 Known filter additives are, for example, diatomaceous earth, natural products resulting from the calcination of diatomite. The main constituents are amorphous SiO_2 modifications, accompanied by oxides of aluminum, iron and other elements, and also their silicate compounds. Perlites are calcined, ground and selected
25 expanded clays of volcanic origin (rhyolites). The structure may be described as sheet-like and chemically as a sodium, potassium or aluminum silicate. Bentonites are clay minerals having high swelling capacity and absorption capacity.
- 30 Filter aids should, during filtration, form a porous environment which takes up the impurities to be eliminated and facilitates the outflow of the liquid phase.

- The additives should have an elevated porosity and should also
35 not deform under the effect of pressure. In addition the substances should be chemically inert and easily recoverable.

- For filtering beer, currently, predominantly kieselguhr precoat filters and depth filters are used. In precoat filtration, before
40 the start of filtration, a kieselguhr precoat is applied to a support surface (filter cloth). After this precoat is applied, a mixture of fine and coarse kieselguhr is added to the beer to be filtered (filter feed). In the production of beer, a kieselguhr consumption of 150 to 200 g/hl of beer must be expected.
- 45 Kieselguhr is particularly proven for precoat filtration because

2

of its high pore volume, its low bulk density, its high absorption capacity and its high specific surface area.

A disadvantage of the use of kieselguhr is that, after a number of filtration operating hours, its effectiveness is exhausted due to retained solids material and it must be removed from the filter support surfaces and replaced.

Landfilling exhausted kieselguhr, owing to legal regulations, is only possible with great difficulty and cost. Attempts to regenerate the kieselguhr which is unusable as filter material have not proved to be feasible in practice. In addition, kieselguhr has been under discussion for some time because of its possible carcinogenic activity.

The removal of materials causing haze, such as dissolved polyphenols or proteins, is also an important process step in many beverage production processes, because removing these substances leads to a longer shelf life of the beverages.

The beverages can be stabilized by adding substances which bind, precipitate or in other ways remove the materials causing the haze from the medium. These substances include, for example, silica gel, which binds or precipitates proteins, or polyvinylpyrrolidone, which binds polyphenols.

Filter aids and stabilizers have previously been used separately or together. In the first case, however, this means increased equipment requirements, and in the second case the joint disposal is a problem; in addition, in the case of the substances previously used, it is not possible to regulate the adsorption.

EP 351 363 describes highly crosslinked polyvinylpolypyrrolidones (PVPP) as stabilizers and filter aids. However, when polyvinylpolypyrrolidone is used alone, it is difficult to adjust the adsorption.

US 4344846 describes a method for precoat filtration using filter aids based on expanded polystyrene.

WO 96/35497 describes regenerable filter aids for filtering a liquid medium, in particular beer, which comprise granules of synthetic or natural polymers that form a filtercake having a porosity from 0.3 to 0.5.

45

3

It is an object of the present invention to provide a filter aid and/or stabilizer which can be used instead of kieselguhr in the filtration and/or stabilization of aqueous liquids, in particular in beer and beverage production. It should not only be usable
5 solely either as filter aid or as stabilizer, but also for both functions as well. It should be insoluble and scarcely swellable, chemically inert and of high surface area, and should be simple to produce in acceptable reaction times. In addition, it should be possible to set the adsorption in targeted manner and it should
10 be regeneratable.

We have found that this object is achieved, surprisingly, by the use of polymers comprising thermoplastic polymers.

15 The invention relates to the use of polymers comprising

(a) from 20 to 95% by weight of at least one thermoplastic polymer

20 (b) from 80 to 5% by weight of at least one further substance selected from the group consisting of silicates, carbonates, oxides, silica gel, kieselguhr, diatomaceous earth, other polymers or mixtures thereof

25 as filter aids and/or stabilizers for filtering and/or stabilizing an aqueous liquid, with the proviso that the thermoplastic polymer must not be polystyrene.

The invention further relates to a process for filtering and/or
30 stabilizing an aqueous liquid, which comprises using as filter aid or stabilizer a polymer comprising

(a) from 20 to 95% by weight of at least one thermoplastic polymer

35

(b) from 80 to 5% by weight of at least one further substance selected from the group consisting of silicates, carbonates, oxides, silica gel, kieselguhr, diatomaceous earth, further polymers or mixtures thereof,

40

with the proviso that the thermoplastic polymer must not be polystyrene.

The process can be carried out in such a manner that in each case
45 only filtration or stabilization of the aqueous medium takes place, or, in addition to the filtration, simultaneous

4

stabilization takes place. Preferably, in addition to the filtration, stabilization also takes place.

During the filtration, the precoat filtration technique is
5 preferably used.

Surprisingly, by means of the inventive polymers, the adsorption of the constituents causing haze in beverages, for example, can be adjusted in a targeted manner.

10

If, for example in the case of beer, the polyphenols present therein are completely removed, the beer also loses by this measure its flavor compounds.

15 A further advantage of the use of the inventive polymers is their regenerability.

For the purposes of the invention the thermoplastic polymers set forth under (a) are amorphous noncrosslinked and partially

20 crystalline noncrosslinked polymers. They are meltable and can be processed by extrusion, injection molding or in a spinning process. They are frequently soluble in organic solvents. They contain not only crystalline but also amorphous regions. The macromolecular chains here pass through a plurality of regions
25 and thus produce the cohesion of the polymer (see also Handbuch der Technischen Polymerchemie [Handbook of industrial polymer chemistry], A. Echte, 1st edition, 1993, VCM, Weinheim). For example, these are taken to mean polyolefins, vinylpolymers, polyamides, polyesters, polyacetates, polycarbonates or else
30 polyurethanes and isomers.

Preferably, the partially crystalline thermoplastics are polyethylene, polyoxymethylene or polypropylene.

The amorphous thermoplastics are preferably polyvinyl chloride or
35 polymethacrylate.

The thermoplastic polymers (a) are used in the context of the invention in amounts of from 20 to 95% by weight, preferably from 40 to 90% by weight, in particular preferably from 60 to 90% by
40 weight, based on the total amount of filter aid.

For the purposes of the invention the carbonates under (b) are alkali metal carbonates or alkaline earth metal carbonates, alkali metal hydrogencarbonates or alkaline earth metal

45 hydrogencarbonates, preferably calcium carbonate, sodium hydrogencarbonate or potassium hydrogencarbonate. Oxides are

5

oxides or mixed oxides of subgroup 4 or subgroup 3, preferably titanium oxide or aluminum oxide.

Silicates are natural and artificial silicates not explicitly referred to above; these also include mixed silicates such as aluminosilicates or else zeolites.

Further polymers under (b) are preferably polyamide or crosslinked polyvinyl lactam and/or polyvinylamine.

- 10 Polyvinyl lactam and/or polyvinylamine preferably used are: polyvinylpyrrolidone, polyvinylpiperidone, polyvinylcaprolactam, polyvinylimidazole, polyvinyl-2-methylimidazole, polyvinyl-4-methylimidazole, polyvinylformamide. Particular preference is given to highly crosslinked
- 15 polyvinylpolypyrrolidone, for example that obtainable under the tradename Divergan® F.

This is customarily obtained by what is termed popcorn polymerization. This is a polymerization method in which the

20 growing polymer chains crosslink with one another. This can take place in the presence or absence of a crosslinker.

Crosslinkers are compounds which contain at least two ethylenically unsaturated non-conjugated double bonds in the

25 molecule. Preferred crosslinkers are divinylbenzene, N,N'-divinylethyleneurea, N,N'-divinylpropylurea, alkylenebisacrylamides, alkylene glycol di(meth)acrylates.

The end product of popcorn polymerization is a foamed, crusty,

30 granular polymer having a cauliflower-like structure. Because of their generally high degree of crosslinking, popcorn polymers are generally insoluble and scarcely swellable.

The epitopes specified under (b) can be present in the filter aid

35 either alone or else in mixtures. Additives used alone are preferably crosslinked polyvinylpyrrolidone, TiO₂, KHCO₃, NaHCO₃, CaCO₃, silica gel, kieselguhr, diatomaceous earth or bentonite. Preferably, mixtures of crosslinked polyvinylpolypyrrolidone (PVPP) with TiO₂, NaHCO₃, KHCO₃, CaCO₃, silica gel, kieselguhr,

40 diatomaceous earth or bentonite or mixtures of NaHCO₃ or KHCO₃ with CaCO₃, TiO₂, silica gel, kieselguhr, diatomaceous earth or bentonite or else mixtures of TiO₂ with NaHCO₃, KHCO₃, CaCO₃, silica gel, kieselguhr, diatomaceous earth or bentonite are used. Crosslinked polyvinylpolypyrrolidone is particularly preferably

45 used.

6

The thermoplastics used can be prepared by processes known per se. Such processes are described, for example, in A. Echte; *Handbuch der Technischen Polymerchemie [Handbook of industrial polymer chemistry]*; VCH, Weinheim, 1993.

5

To produce the polymer powders, the thermoplastic polymers and at least one further substance are compounded in an extruder.

- Compounding is generally mixing a polymer with at least one additive (*Der Doppelschneckenextruder : Grundlagen- und Anwendungsgebiete [The double-screw extruder: principle and areas of application]*, edited by: VDI-Gesellschaft Kunststofftechnik - Düsseldorf: VDI-Verlag, 1995, chapter 7 and *Aufbereiten von Polymeren mit neuartigen Eigenschaften [Compounding polymers having novel properties]*, edited by: VDI-Gesellschaft Kunststofftechnik - Düsseldorf: VDI-Verlag, 1995, pp. 135 ff.). Compounding polymers by filling and reinforcing is carried out in the case of polyolefins and polystyrene, for example, for specific improvement of the properties and to reduce the manufacturing costs. The fillers may be differentiated according to their particle geometry by the aspect ratio. If the value is less than 10, the substance is a pure filler (extender), and a reinforcing action is usually only achieved at higher values. This effect can be reinforced by pronounced adhesion forces between additive and polymer. Fillers frequently used are calcium carbonate (chalk) and talcum. Because of its approval for food, calcium-carbonate-filled polypropylene has also been widely used for food packages (injection molding, thermoforming). In addition, filling polypropylene with sawdust is described for sheets which are used in automobile construction. Other customary fillers are glass (for example in bead form), asbestos, silicates (for example wollastonite), mica, spars and graphite. A usual filler content is 20-80% by mass, but it can also be up to 95%. By reinforcing thermoplastics with fibrous substances the mechanical properties are improved, in particular rigidity and hardness of the plastic. The fibers customarily used are glass fibers, carbon fibers, steel fibers and aramid fibers. By mixing at least two plastics, blending polymers having a different property profile are obtained. The mixtures can be homogeneous, heterogeneous or of partial or limited compatibility.

In all cases the use of extruders, in particular twin-screw extruders, is preferred. In addition, however, cokneaders also occur.

45

7

Customarily, during extrusion temperatures and pressures occur which, in addition to the purely physical mixing, can make possible a chemical reaction, that is to say a chemical change in the starting components.

5

For the purposes of the invention, reaction is a process in which at least two substances are reacted with one another physically and/or chemically.

- 10 The reaction can also take place by the customary processes for processing thermoplastics, in particular mixing, dispersing, filling, reinforcing, blending, degassing, and reactive compounding by rolling, kneading, casting, sintering, pressing, compounding, calendering, extrusion or combination of these
15 methods. However, preferably, the polymer powders are compounded in an extruder.

For the purposes of the invention, filtration is passing a suspension (slurry) consisting of a discontinuous phase

- 20 (dispersed substances) and a continuous phase (dispersion medium) through a porous filter medium. During this operation, solids particles are deposited on the filter medium and the filtered liquid (filtrate) leaves the filter medium in a clear state. An applied pressure difference acts here as an external force to
25 overcome the resistance to flow.

- In the filtration operation, fundamentally differing solids separation mechanisms can be observed. Chiefly, these are surface filtration or cake filtration, depth filtration and screening
30 filtration. Frequently, filtration involves a combination of at least two processes.

- In the case of surface or cake filtration, what are termed precoat filters in various embodiments are used for beverage
35 filtration (Kunze, Wolfgang, Technologie Brauer und Mälzer [Brewing and malting technology], 7th edition, 1994, p. 372). All precoat systems share the fact that the solids present in the liquid to be filtered and also the intentionally added solids (filter aids) are retained by a filter medium, a filter cake
40 building up. The suspension must flow through this in the course of filtration, in addition to the filter medium. Filtration of this type is also termed precoat filtration.

8

For the purposes of the invention, liquids to be filtered and/or stabilized are fruit juices or fermented beverages, such as wine or beer. In particular, the inventive process is used for filtering and/or stabilizing beer.

5

The inventively prepared filter aids and/or stabilizers are distinguished by high wettability with water and constant flow rate with, at the same time, good filtration efficiency.

10 The filter aids are comminuted after the mixing process by pelletizing, shredding and/or grinding, preferably by a sequence of pelletizing and grinding. Under the temperature conditions of a cold-grinding process, water may remain in the final product.

15 The resultant powders have a mean particle size of from 1 to 1000 μm , preferably from 2 to 200 μm . They have either an irregular or regular structure, which may be spheroidal or nonspheroidal. However, preferably, the resultant powders are nonspheroidal.

20

The examples below are intended to describe the invention in more detail, but without restricting it thereto.

A) Production of polymer powders

25

A thermoplastic polymer and at least one further substance (total amount approximately 10 kg) are compounded in an extruder. The extrudate is cooled in a water bath and pelletized. The resultant pellets are comminuted in an impact disk mill and screened using

30 a vibrating tumble screen.

The weight ratios in which the thermoplastic polymer and respective additives (substance 1, where appropriate also substance 2) have been compounded is given by the table below.

35 The sample identification is given in brackets after the weight ratio.

40

45

#	Thermoplastic polymer	Substance 1	Substance 2	Ratio of thermoplastic polymer: substance 1
				(where appropriate: substance 2)
5	1 polypropylene	kieselguhr	-	20:80 (1a); 50:50 (1b); 80:20 (1c); 90:10 (1d)
	2 polypropylene	CaCO ₃	-	60:40 (2a); 80:20 (2b)
	3 polypropylene	TiO ₂	-	60:40 (3a); 80:20 (3b)
	4 polypropylene	PVPP	-	60:40 (4a); 80:20 (4b)
	5 polypropylene	silica gel	-	80:20 (5a)
10	6 polypropylene	bentonite	-	80:20 (6a)
	7 polypropylene	PVPP	silica gel	70:25:5 (7a); 70:28:2 (7b)
	8 polyethylene	kieselguhr	-	50:50 (8a); 80:20 (8b); 90:10 (8c)
15	9 polyethylene	CaCO ₃	-	60:40 (9a); 80:20 (9b)
	10 polyethylene	TiO ₂	-	60:40 (10a); 80:20 (10b)
	11 polyethylene	PVPP	-	60:40 (11a); 80:20 (11b)
	12 polyethylene	silica gel	-	80:20 (12a)
	13 polyethylene	bentonite	-	80:20 (13a)
20	14 polyethylene	PVPP	silica gel	70:25:5 (14a); 70:28:2 (14b)
	15 polyamide	kieselguhr	-	20:80 (15a); 50:50 (15b); 80:20 (15c); 90:10 (15d)
	16 polyamide	CaCO ₃	-	60:40 (16a); 80:20 (16b)
	17 polyamide	TiO ₂	-	60:40 (17a); 80:20 (17b)

25

In the table:

Polypropylene: denotes Novolen, BASF

Polyethylene: denotes Lupolen®, BASF

30 Polyamide: denotes Ultramid®, BASF

Kieselguhr: denotes kieselguhr, Merck, CAS No. 68855-54-9;

CaCO₃: denotes calcium carbonate (precipitated, ultrapure), Merck, CAS No. 471-34-1;

35 TiO₂: denotes titanium dioxide (<325 mesh, 99%), Aldrich, CAS No. 1317-70-0;

PVPP: denotes Divergan F, BASF, CAS No. 9003-39-8;

NaHCO₃: denotes sodium hydrogencarbonate (ultrapure), Merck, CAS No. 144-55-8;

Silica gel: denotes silica gel, Merck, CAS No. 63231-67-4;

40 Bentonite: denotes bentonite, Aldrich.

B) Application tests

Filtration of a standard turbidity solution

45 The filtration efficiency is assessed in precoat filtration on the basis of clarification of a standard turbidity solution, that is a formazine solution of defined turbidity which is known to

10

those skilled in the art for characterizing filter aids for the beverage industry.

The criteria of a good test result are constancy of flow rate and
5 of precoat pressure and the filtration efficiency, that is to say clarity of the filtrate:

the precoat pressure upstream and downstream of the filter is the same when the flow through the filter is good, that is to say there is no plugging of the filter. Turbidity is determined by a
10 standard EBC test. A liquid is judged to be clear when the EPC turbidity values are < 1 .

Below, studies are described using the polymer samples described in section A. Here, preferably, the grinding fraction having a
15 particle size less than $100\text{ }\mu\text{m}$ is used.

The table shown below reports the values after passage of a volume of 5 l, 10 l and 15 l for selected samples.

20 Filtration efficiency and flow through the filter

Sample	1c	11b
EBC turbidity ¹⁾ ²⁾ after passage of a volume of		
25 5 l	2.51	1.78
10 l	1.41	1.25
15 l	0.92	0.76
Flow rate ³⁾ (l h^{-1})	40 ⁴⁾	40 ⁴⁾
Precoat pressure ⁵⁾ (bar) (upstream/downstream of filter body)	1.5 ⁴⁾ /1.5 ⁴⁾	1.5 ⁴⁾ /1.5 ⁴⁾

1) EBC: European Brewery Convention.

2) The zero value, that is to say the value of the standard
35 turbidity solution is 20 EBC.

3) The flow rate without a filter aid is 40 l h^{-1} .

4) The measured value is constant during the entire filtration period.

5) The precoat pressure of the pure liquid, that is to say
40 without filter aid, is 1.5 bar.

Use of polymers comprising thermoplastic polymers as filter aids and/or stabilizers

5 Abstract

A description is given of the use of polymers comprising thermoplastic polymers as filter aids and/or stabilizers for filtering or stabilizing aqueous liquids.

10

15

20

25

30

35

40

45